

Complete Analytical Solution ISO 14001: 2015 & ISO 9001: 2015 Certifified

SHREE RAM TESTING LABORATORIES

ISO 14001: 2015 & ISO 9001: 2015 Approved Laboratory

Lab: A-2/103, Site-V, UPSIDC Industrial Area, Kasna, Greater Noida-201306 H.O. 223, 2nd Floor, Living Style Mall, Jasola, New Delhi-110025 Mob: 9953984801, 9717160780, 9999024801, E-mail: stl.noida@gmail.com

E-mail: info@shreeramlab.com, shreeramlab@yahoo.com, Website: www.shreeramlab.in

TEST REPORT

Issued to : M/S Siddhi Rubber Udyog

SHREE RAM TESTING LAB Plot No-C-127, Sector-10

SHREE RAM TESTING LAE Noida Gautam Buddha Nagar(U.P)

Report No. MS-190522-01

Report date: 25/05/2022 Sample Received: 19/05/2022

Analysis date: 19/05/2022 to 25/05/2022

Sampled By: Customer

Sample Description: Geo-Textile

SHREE RAM TESTING Size:- SN -250 GSM

P- 1/1

RESULTS

Sr. No.	Parameters	Test Method	Unit	Result
1cam Ram	Extension at break (5)	DIN EN 53857/2	%	94 DRAFORI
2	Unit- Weight	DIN EN 53854	G/m²	254 ORATORI
3 (a)	Thickness at 0.02 bar	DIN EN 53855/3	mm	4.5 BORATORIE
(b)	Thickness at 2.0 bar	DIN EN 53855/3	mm	2.4 2.4 A TORN
PAM RAM	Tensile Strength	DIN EN 53857/2	N/cm ²	1344
RAM RAM	Extension at 30 % of tensile strength	DIN EN 53857/2	%	RAM PETING LABORATORIE
RAM RAM	Resistance against acid & alkaline solution, pH 2-13	DIN EN 53857/2	% 548	PAM TESTING AROSATORI
RAM	Permeability in plane @ 0.02 bar & 2.00 Bar	ASTM D 4491	%	RAM TESTIN 22 ABORATORIE
(a) w	at 0.02 baronatones	ASTM D 4491	Cm/s	5 x 10^-1 FATORII
b)	at 2.00 Bar	ASTM D 4491	Cm/s	5 x 10^-2
RAM	Resistance to punching	DIN EN 54307	N SHREE	2024 ORATORI

END OF REPORT

Note:- (1) The above results are related only to the test performed on the sample, Endorsement to product is neither inferred. (2) This report is not to be reproduced wholly or in part & can not be used as an evidence in the court of law & should not be used in a any advertising media without special permission in writing (3) Sample will be destroyed after 30 days from the date of reporting unless otherwise specified. (4) Total liability of our lab is limited to the invoice amount (5) report refers to the sample drawn by shree ram testing Laboratories unless mentioned otherwise