

SHREE RAM TESTING LABORATORIES

ISO 14001: 2015 & ISO 9001: 2015 Approved Laboratory

Lab: A-2/103, Site-V, UPSIDC Industrial Area, Kasna, Greater Noida-201306 H.O. 223, 2nd Floor, Living Style Mall, Jasola, New Delhi-110025 Mob: 9953984801, 9717160780, 9999024801, E-mail: stl.noida@gmail.com E-mail: info@shreeramlab.com, shreeramlab@yahoo.com, Website: www.shreeramlab.in

TEST REPORT

Issued to : M/S Siddhi Rubber Udyog Plot No-C-127, Sector-10 SHRE RAM TESTING LA Noida Gautam Buddha Nagar(U.P)

Report No. MS-190522-01 Report date: 25/05/2022 Sample Received: 19/05/2022 Analysis date: 19/05/2022 to 25/05/2022 Sampled By: Customer

Sample Description: Geo-Textile

SHREE EAM TEERING LABORATORIES

SHREE RUM TESTING LABORATORIES SHREE RAW TESTING LABORATORIES

Size:- SN-300 GSM

P-1/1

RESULTS

Sr. Parameters Test Method Unit Res				
No.	PESTANG ESRONATORIES	rest iviethod	Unit	Result
TAM.	Extension at break	DIN EN 53857/2	%	94
2	Unit- Weight	DIN EN 53854	G/m²	304
3 (a)	Thickness at 0.02 bar	DIN EN 53855/3	mm	4.5
(b)	Thickness at 2.0 bar	DIN EN 53855/3	mm	2.4
4	Tensile Strength	DIN EN 53857/2	N/cm²	9.5
5	Extension at 30 % of tensile strength	DIN EN 53857/2	%	27 US A 10
6	Resistance against acid & alkaline solution, pH 2-13	DIN EN 53857/2	%	7.7 - 7.7 - SATORATO
7	Permeability in plane @ 0.02 bar & 2.00 Bar	ASTM D 4491	%	22
(a)	at 0.02 bar	ASTM D 4491	Cm/s	5 x 10^-1
(b)	at 2.00 Bar	ASTM D 4491	Cm/s	5 x 10^-2
8	Resistance to punching	DIN EN 54307	N	2024

********** **END OF REPORT**

Note:- (1) The above results are related only to the test performed on the sample, Endorsement to product is neither inferred. (2) This report is not to be reproduced wholly or in part & can not be used as an evidence in the court of law & should not be used in a any advertising media without special permission in writing (3) Sample will be destroyed after 30 days from the date of reporting unless otherwise specified. (4) Total liability of our lab is limited to the invoice amount (5) report refers to the sample drawn by shree ram testing Laboratories unless mentioned otherwise