

SHREE RAM TESTING LABORATORIES

ISO 14001: 2015 & ISO 9001: 2015 Approved Laboratory

Lab: A-2/103, Site-V, UPSIDC Industrial Area, Kasna, Greater Noida-201306
H.O. 223, 2nd Floor, Living Style Mall, Jasola, New Delhi-110025
Mob: 9953984801, 9717160780, 9999024801, E-mail: stl.noida@gmail.com
E-mail: info@shreeramlab.com, shreeramlab@yahoo.com, Website: www.shreeramlab.in

Complete Analytical Solution ISO 14001 : 2015 & ISO 9001 : 2015 Certifified

## TEST REPORT

E RAM TESTING LABORATORIES			SHREE RAM TESTING LABORATORIES		
Issued to: M/S	Siddhi Rubber udyog		Report No.	AM TESTING LAIMS-161122-04	
E RAM TESTING LA	Unit C-127, sector-10, Noida 201301 (UP) India 09CBHPK1466J2ZC	*	Report Date:	17/11/2022	
			Sample Received:	AM TESTING LABOR16/11/2022	
			Analysis Date:	16/11/2022 to 17/11/2022	
			Sample by:	Customer	

Sample Description: Coir Green Blankets 450 GSM

SHREE RAM TESTING LABORP-1/1/ES

## RESULTS

S.No.	Parameters	Unit	Test Method	Result
1AM TE	Thickness	mm	ASTM D 5199	12
2 4/17	Mass per unit Area	g/m²	ASTM D5261	463
3 A M TE	Elongation at Break	%	ASTM D 4632	ABORA 34
4 <sub>AM</sub> TE	Tensile Strength (MD)	N/m	ASTMD 4595	LABOR 8.3
5	Tensile Strength (CD)	N/m	ASTMD 4595	5.8

**END OF REPORT** 

SHARE TESTED BY

SHARE

SHARE

TESTED BY

SHARE

SHARE

SHARE

SHREE RAM TESTING LABORATORIES SHREE RAM TESTING LABORATORIES SHREE RAM TESTING LABORATORIES AUTHORIZED SIGNATORY

SHREE RAM TESTING LABORATORIES

Note:- (1) The above results are related only to the test performed on the sample, Endorsement to product is neither inferred. (2) This report is not to be reproduced wholly or in part & can not be used as an evidence in the court of law & should not be used in a any advertising media without special permission in writing (3) Sample will be destroyed after 30 days from the date of reporting unless otherwise specified.

(4) Total liability of our lab is limited to the invoice amount (5) report refers to the sample drawn by shree ram testing Laboratories unless mentioned otherwise